



## Aggregate Technical Data Sheet

TruStride™ · LiteStride™ · SteadiGait™ · EquiBlend™ · SoftShoe™

### IDEAL SILICA SAND SPECIFICATION

<b>SiO<sub>2</sub> Content</b>	95–99% minimum
<b>Clay Content</b>	Less than 1.5%
<b>Grain Shape</b>	Angular to sub-angular
<b>Color</b>	Light
<b>Average Sieve Size</b>	110 microns (range: 70–180 microns)

Sand quality and particle properties are critical to long-term wax adhesion and arena surface performance. IGK sources aggregate to meet or exceed the above specification for all TruStride™, LiteStride™, SteadiGait™, and EquiBlend™ product lines. For pre-installation consultation, contact IGK Equestrian at [igkequestrian.com](http://igkequestrian.com).